



# Perforirani limovi od inoksa Lamiere forate in inox Perforated plates in inox

Kvalitet Qualita' Quality	Cmax	Cr	Ni	Mn max	P max	S max	Si max	Mo	Rm N/mm2	Rp 0,2 N/mm2	Alon
AISI 304 (1.4301)	0,07	17-19,5	8-10,5	2	0,045	0,015	1		500-700	195 min	35 min
AISI 316 (1.4401)	0,07	16,5-18,5	10-13	2	0,045	0,015	1	2-2,5	510-710	205 min	40 min

## Okrugle izmjenične perforacije/ Fori Tondi alternati / Alternated Round Perforations

Diametar rupa Diametro fori Diamet.of holes (mm)	Debljina / Spessore / Thickness (mm)				
	0,5	1	1,5	2	3
1	♦	♦			
1,5	♦				
2	♦	♦			
2,5			♦	♦	
3				♦	
4			♦	♦	♦
5					♦
6				♦	
8	♦	♦	♦	♦	♦
10	♦	♦	♦		

## Jednake Kvadratne perforacije / Fori Quadri Pari / Equal Square Perforations

Diametar rupa Diametro fori Diamet.of holes (mm)	Debljina / Spessore / Thickness (mm)				
	0,5	1	1,5	2	3
5 × 5		♦			
10 × 10		♦			